

## Technical data

|   |                                      |                |
|---|--------------------------------------|----------------|
| Click system  | <b>UNILIN</b>                        |                |
| Size  | <b>225 x 1220 mm   400 x 800 mm</b>  |                |
| Total thickness   | <b>6 mm</b>                          |                |
| Backing   | <b>1,5 mm EVA + PE</b>               |                |
| Wear layer  | <b>0,55 mm</b>                       |                |
| Bevel   | <b>Microbevel   Painted V-bevel</b>  |                |
| Classification EN429  | <b>33 / 42</b>                       |                |
| Wear group EN649:2011   | <b>T</b>                             |                |
| Colour fastness to light EN ISO105 B02:2014   | <b>6</b>                             |                |
| Dimensional stability ISO23999:2018   | Manufacturing direction              | <b>0,05 %</b>  |
|   | Across-manufacturing direction       | <b>0,015 %</b> |
| Curling after heat exposure ISO23999:2018   | <b>0 mm</b>                          |                |
| Fire behavior EN 13501-1-2018 Clause 9, EN ISO 9239-1:2010, EN ISO 11925-2:2010,COR1-2011 | <b>Bfl-s1</b>                        |                |
| Slip resistance DIN 51130:2014-02   | <b>R10</b>                           |                |
| Castor chair test EN ISO 4918:2016  | <b>PASS</b>                          |                |
| Determination of residual indentation EN ISO 24343-1:2007 (R2015)                         | <b>&lt; 0,21 mm</b>                  |                |
| Staining and resistance to chemicals EN 26987:2012  | <b>PASS</b>                          |                |
| Dynamic coefficient of friction on dry floor surface EN 13893:2002                        | <b>DS (≥ 0,30°)</b>                  |                |
| Movement of furniture leg resistance EN 424:2001  | <b>PASS</b>                          |                |
| VOC emission testing EN ISO 16000-9:2006 / COR-1-2007, ISO 16000-6:2001                   | <b>A+</b>                            |                |
| Thermal conductivity and thermal resistance EN 12664:2001                                 | <b>0,106 W/(m.K)   0,057(m².K)/W</b> |                |
| Improvement of impact sound ISO 10140-1:2016  | <b>19 dB</b>                         |                |
| Sound insulation ISO 717-2:2013   | <b>19 dB</b>                         |                |
| Warranty domestic use*  | <b>20</b>                            |                |
| Warranty comercial use*   | <b>10</b>                            |                |